

Sub B' /
a 30 to 80 nm layer of amorphous silicon or polycrystalline silicon having a first particle diameter on a substrate, and irradiating said substrate with an energy beam to convert said semiconductor thin film to polycrystalline silicon having a larger particle diameter than said first particle diameter,

A' Cont.
a thin film transistor is integrated and formed in a prescribed region by using said semiconductor thin film thus converted to polycrystalline silicon as an active layer, and

a cross sectional shape of said energy beam is adjusted with respect to said region to irradiate said region at a time by a single shot irradiation, so that characteristics of said thin film transistor is made uniform.

12. (amended) A display device comprising a pair of substrates adhered to each other with a prescribed gap, and an electrooptical substance maintained in said gap, one of said substrates comprises a counter electrode, the other substrate comprises a pixel electrode and a thin film transistor driving said pixel electrode, and said thin film transistor comprises a semiconductor thin film and a gate electrode accumulated on one surface of said semiconductor thin film through a gate insulating film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of amorphous silicon or polycrystalline silicon having a first particle diameter on said other

Sub B1
A' Cond.
substrate, and irradiating said other substrate with an energy beam to convert said semiconductor thin film to polycrystalline silicon having a particle diameter that is larger than said first particle diameter,

a thin film transistor is integrated and formed in a prescribed region by using said semiconductor thin film thus converted to polycrystalline silicon as an active layer, and

a cross sectional shape of said energy beam is adjusted with respect to said region to irradiate said region at a time by a single shot irradiation, so that characteristics of said thin film transistor is made uniform.

Sub B2
A2
17. (amended) A thin film semiconductor device comprising a semiconductor thin film, a gate insulating film accumulated on one surface thereof, and a gate electrode accumulated on said semiconductor thin film through said gate insulating thin film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of amorphous silicon or polycrystalline silicon having a first particle diameter on a substrate, on which plural units are formed, and intermittently irradiating said substrate, so as to convert to polycrystalline silicon having a particle diameter that is larger than said first diameter,

a cross sectional shape of said energy beam is adjusted

with respect to said unit to irradiate one or two or more units at a time by a single shot irradiation, and

a thin film transistor is integrated and formed in said units thus subjected to irradiation at a time.

Sub B27
As cont.
18. (amended) A display device comprising a pair of substrates adhered to each other with a prescribed gap, and an electrooptical substance maintained in said gap, one of said substrate comprises a counter electrode, the other substrate comprises a pixel electrode and a thin film transistor driving said pixel electrode, and said thin film transistor comprises a semiconductor thin film and a gate electrode accumulated on one surface of said semiconductor thin film through a gate insulating film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of amorphous silicon or polycrystalline silicon having a first particle diameter on a substrate, on which plural units are formed, and intermittently irradiating said substrate, so as to convert said semiconductor thin film to polycrystalline silicon having a larger particle diameter than said first diameter,

a cross sectional shape of said energy beam is adjusted with respect to said unit to irradiate one or two or more units at a time by a single shot irradiation, and

a thin film transistor is integrated and formed in said

A2
conf. units | thus subjected to irradiation at a time.

Sub B3 7
27. (amended) A thin film transistor having a laminated structure comprising a semiconductor thin film, a gate insulating film accumulated on one surface thereof, and a gate electrode accumulated on said semiconductor thin film through said gate insulating thin film,

A3
wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of amorphous silicon or polycrystalline silicon having a first particle diameter on a substrate, and irradiating a prescribed region of said substrate with laser light having a prescribed cross sectional shape to convert said semiconductor thin film to polycrystalline silicon having a larger particle diameter than said first diameter, and

said semiconductor thin film is accumulated by alternately repeating said film forming step and said irradiation step without exposing said substrate to the air.

28. (amended) A display device comprising a pair of substrates adhered to each other with a prescribed gap, and an electrooptical substance maintained in said gap, one of said substrate comprises a counter electrode, the other substrate comprises a pixel electrode and a thin film transistor driving said pixel electrode, and said thin film transistor comprises a semiconductor thin film and a gate electrode accumulated on

Sub B3
one surface of said semiconductor thin film through a gate insulating film,

A3
COR'd.
wherein said semiconductor thin film is formed by forming a layer of about 20 nm amorphous silicon or polycrystalline silicon having a first particle diameter on a substrate, and irradiating a prescribed region of said substrate with laser light having a prescribed cross sectional shape to convert to polycrystalline silicon having a larger particle diameter than said first diameter, and

said semiconductor thin film[s are] is accumulated by alternately repeating said film forming step, where each additional formed film is about 1 nm, and said irradiation step without exposing said substrate to the air.

Sub B4
A4
39. (amended) A thin film transistor having a laminated structure comprising a semiconductor thin film, a gate insulating film accumulated on one surface thereof, and a gate electrode accumulated on said semiconductor thin film through said gate insulating film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on a substrate, and irradiating a prescribed region of said substrate one or more with a pulse of laser light having a constant cross sectional area and an emission time width from upstand to downfall of 50 ns or more, so as to convert said

Sub B47
non-single crystal silicon contained in an irradiated area corresponding to said cross sectional area to a polycrystalline silicon at a time, and

a desired change to said energy intensity of said laser light from upstand to downfall of said pulse is applied to said polycrystalline silicon.

A4 cont.
40. (amended) A display device comprising a pair of substrates adhered to each other with a prescribed gap, and an electrooptical substance maintained in said gap, one of said substrate comprises a counter electrode, the other substrate comprises a pixel electrode and a thin film transistor driving said pixel electrode, and said thin film transistor comprises a semiconductor thin film and a gate electrode accumulated on one surface of said semiconductor thin film through a gate insulating film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on said other substrate, and irradiating a prescribed region of said substrate once or more with a pulse of laser light having a constant cross sectional area and an emission time width from upstand to down fall of 50 ns or more, so as to convert said non-single crystal silicon contained in an irradiated area corresponding to said cross sectional area to a polycrystalline silicon at a time, and

A4
cond. a desired change to said energy intensity of said laser light from upstand to downfall of said pulse is applied to said polycrystalline silicon.

Sub
B5 7 53. (amended) A thin film transistor having a laminated structure comprising a semiconductor thin film, a gate insulating film accumulated on one surface thereof, and a gate electrode accumulated on said semiconductor thin film through said gate insulating film,

A5 wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on a substrate, and irradiating a prescribed region of said substrate once or more with a pulse of laser light having a constant cross sectional area and an emission time width of 50 ns or more with maintaining said substrate in a non-oxidative atmosphere, so as to convert said non-single crystal silicon contained in an irradiated area corresponding to said cross sectional area to a polycrystalline silicon at a time.

54. (amended) A display device comprising a pair of substrates adhered to each other with a prescribed gap, and an electrooptical substance maintained in said gap, one of said substrate comprises a counter electrode, the other substrate comprises a pixel electrode and a thin film transistor driving said pixel electrode, and said thin film transistor comprises

Sub B5
a semiconductor thin film and a gate electrode accumulated on one surface of said semiconductor thin film through a gate insulating film,

A5
cond.
wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on said other substrate, and irradiating a prescribed region of said substrate once or more with a pulse of laser light having a constant cross sectional area and an emission time width of 50 ns or more with maintaining convert said non-single crystal silicon contained in an irradiated area corresponding to said cross sectional area to a polycrystalline silicon at a time.

Sub B6
A6
63. (amended) A thin film transistor having a laminated structure comprising a semiconductor thin film, a gate insulating film accumulated on one surface thereof, and a gate electrode accumulated on said semiconductor thin film through said gate insulating film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on a substrate, and irradiating a prescribed region of said substrate once or more with a pulse of laser light having a constant cross sectional area and an emission time width of 50 ns or more under conditions in that said substrate is uniformly heated, so as to convert said non-single crystal silicon contained in an irradiated area corresponding to said

Ab
cond. cross sectional area to polycrystalline silicon at a time.

Sub B7
A7 65. (amended) A display device comprising a pair of substrate adhered to each other with a prescribed gap, and an electrooptical substance maintained in said gap, one of said substrate comprises a counter electrode, the other substrate comprises a pixel electrode and a thin film transistor comprises a semiconductor thin film and a gate electrode accumulated on one surface of said semiconductor thin film through a gate insulating film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on said other substrate, and irradiating a prescribed region of said substrate once or more with a pulse of laser light having a constant cross sectional area and an emission time width of 50 ns or more under conditions in that said other substrate is uniformly heated, so as to convert said non-single crystal silicon contained in an irradiated area corresponding to said cross sectional area to a polycrystalline silicon at a time.

Sub B8
A8 73. (amended) A thin film transistor having a laminated structure comprising a semiconductor thin film, a gate insulating film accumulated on one surface thereof, and a gate electrode accumulated on said semiconductor thin film through said gate insulating film,

Sub B87
A8
wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on a substrate, and irradiating a prescribed region of said substrate once or more with a pulse of laser light having a constant cross sectional area and an emission time width of 50 ns or more under conditions in that said substrate is cooled to a temperature lower than room temperature, so as to convert said non-single crystal silicon contained in an irradiated area corresponding to said cross sectional area to a polycrystalline silicon at a time.

74. (amended) A display device comprising a pair of substrates adhered to each other with a prescribed gap, and an electrooptical substance maintained in said gap, one of said substrates comprises a counter electrode, the other substrate comprises a pixel electrode and a thin film transistor driving said pixel electrode, and said thin film transistor comprises a semiconductor thin film and a gate electrode accumulated on one surface of said semiconductor thin film through a gate insulating film,

wherein said semiconductor thin film is formed by forming a 30 to 80 nm layer of non-single crystal silicon on said other substrate, and irradiating a prescribed region of said substrate once or more with a pulse of laser light having a constant cross sectional area and an emission time width of 50